



To

L'ISOLANTE K.FLEX S.r.l.

Via Don G. Locatelli, 35

20040 RONCELLO (MI)

Date, 18<sup>th</sup> May, 2009

TR n° 261-C<sub>bis</sub>/2009

Ref. Your Ord.n°CE 09 022 dated 30.04.2009

Received 07.05.2009

Start tests 11.05.2009

End tests 15.05.2009

Page 1 of 1

# T E S T R E P O R T

**Subject:** DETERMINATION OF THE TEAR RESISTANCE OF THE PRODUCT "K-Flex AL Clad Foil"

PRODUCT

K-Flex AL Clad Foil

Test Method

Tear resistance

N/mm

115,4

ASTM D 1004:2003

Speed of testing: 50 mm/min

The sampling has been carried out by the Customer.

The contained results refer only to the tested sample.

This report cannot be partially reproduced without the laboratory approval.

C. Montà, *Operator*

F. Casa, *Director*