



To

L'ISOLANTE K.FLEX S.r.l.

Via Don G. Locatelli, 35

20040 RONCELLO (MI)

Date, 18<sup>th</sup> May, 2009

TR n° **261-B<sub>bis</sub>/2009**

Ref. Your Ord.n°CE 09 022 dated 30.04.2009

Received 07.05.2009

Start tests 11.05.2009

End tests 15.05.2009

Page 1 of 1

# T E S T R E P O R T

**Subject:** DETERMINATION OF THE TENSILE ELASTIC MODULUS OF THE PRODUCT  
"K-Flex AL Clad Foil"

PRODUCT

K-Flex AL Clad Foil

Test Method

Elastic modulus in strain

MPa

3080


UNI EN ISO 527-1:1997

Test pieces: Strips 150x25x0,30 mm  
Speed of testing : 1 mm/min

The sampling has been carried out by the Customer.

The contained results refer only to the tested sample.

This report cannot be partially reproduced without the laboratory approval.

  
C. Montà, *Operator*

  
F. Casa, *Director*